

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(43) International Publication Date
14 October 2004 (14.10.2004)

PCT

(10) International Publication Number
WO 2004/087573 A1(51) International Patent Classification⁷: C01B 39/02,
39/46(21) International Application Number:
PCT/AU2004/000428

(22) International Filing Date: 2 April 2004 (02.04.2004)

(25) Filing Language: English

(26) Publication Language: English


(30) Priority Data:
2003901594 4 April 2003 (04.04.2003) AU(71) Applicant (for all designated States except US):
NANOCHEM HOLDINGS PTY LTD [AU/AU];
Level 6 Gehrman Laboratories, Research Road, Univer-
sity of Queensland, St Lucia, QLD 4070 (AU).

(72) Inventors; and

(75) Inventors/Applicants (for US only): MACKINNON,
Ian [AU/AU]; c/- Level 6 Gehrman Laboratories, Re-
search Road, University of Queensland, St Lucia, QLD
4000 (AU). MILLAR, Graeme [GB/AU]; c/- Level 6Gehrman Laboratories, Research Road, University of
Queensland, St Lucia, QLD 4070 (AU). STOLZ, Wanda
[AU/AU]; c/- Level 6 Gehrman Laboratories, Research
Road, University of Queensland, St Lucia, QLD 4070
(AU).(74) Agent: FISHER ADAMS KELLY; Level 13 AMP Place,
10 Eagle Street, Brisbane, QLD 4000 (AU).(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,

[Continued on next page]

(54) Title: ALUMINOSILICATES OF ZEOLITE N STRUCTURE



(57) Abstract: A process for making aluminosilicates of zeolite N structure comprising the steps of: (i) combining a water soluble monovalent cation, a solution of hydroxyl anions and an aluminosilicate to form a resultant mixture having a pH greater than 10 and a H₂O/Al₂O₃ ratio in the range 30 to 220; (ii) heating the resultant mixture to a temperature of between 50°C and the boiling point of the mixture for a time between 1 minute and 100 hours until a crystalline product of zeolite N structure is formed as determined by X-ray diffraction or other suitable characteristic; and (iii) separating the zeolite N product as a solid from the mixture.